



APPLICATION

Upholstery/decoration

COMPOSITION

70% CO, 15% PC, 8% PL, 5% WO, 2% PA

WIDTH

140 cm

WEIGHT

700 GR/MTL

TARIFF CODE

52111100

DIMENSIONAL STABILITY

DRY CLEANING

ISO 3175-2:2010

TRAMA / WEFT: -1.4%, ORDITO /WARP: -1.6% / -1.4%

MACHINE WASHING 30°

UNI EN ISO 6330:2012 + 3759:2011 + 5077:2008

TRAMA / WEFT: -2.3% / -2.1%, ORDITO /WARP: -1.2%

COLOUR FASTNESS

DRY RUBBING

UNI EN ISO 105 X 12:2016, 4-5

WET RUBBING

UNI EN ISO 105 X 12:2016, 4-5

LIGHT FASTNESS

UNI EN ISO 105 B02:2014, 4-5

TECHNICAL CHARACTERISTIC

PILING

UNI EN ISO 12945-2:2002, 3/4

TEAR STRENGTH

ISO 13937-3:2002, TRAMA / WEFT: N.D., ORDITO /WARP: N.D.

TENSILE STRENGTH

ISO 13934-2, TRAMA / WEFT : 500 N, ORDITO /WARP: 420 N

SEAM SLIPPAGE

EN ISO 13936-2, TRAMA / WEFT: 5.4 mm, ORDITO /WARP: 12.1 mm

RESISTANCE TO ABRASION / MARTINDALE

UNI EN ISO 12947-1:2000 + 12947-2:2000, 25000, End point at rubs

FIRE TREATMENT BS 5852

CIGARETTE TEST

BS 5852-1:1979, PASS

BUTANE FLAME

BS 5852-1:1979, NOT PASS

CAL 117:

TB 117:2013, PASS

The overmentioned numbers represent average values communicated in good faith, but they cannot be considered as a contract document. Consider if the application is appropriate before choosing this fabric, as the product cannot be held responsible when improperly used. There may be slight colour variations between batches.



